

Product (#)

2-20/3-20(#1)



Wet Weight Split 1	1865
Dry Weight Split 1	1804
Moisture Content	3.4%
Wet Weight Split 2	1945
Dry Weight Split 2	1879

Sample #	May 9 2024
Date & Time Sampled	May 9 2024
Sampled By	BSG
Date & Time Tested	May 9 2024
Tested By	BSG
Pit Location	Edberg

Sieve Number	Weight Retained	Fractured Weight	% Passing	Lower Limit	Upper Limit
25000	0	0	100.0	100	100
20000	0	0	100.0	100	100
12500	355	246	81.1	60	96
5000	653	552	46.4	36	75
2000	155		38.1	24	54
1250	52		35.3	20	43
630	117		29.1	14	34
400	187		19.2	11	29
315	107		13.5	9	26
160	127		6.7	6	20
80	77		2.6	2	10
Pan	48				

Fractures (5mm +)	(min 50%)
Sieve Weights	1008
Fractured Weight	798
	79.2%

