

Pan:

16114 114 Ave NW Edmonton, Alberta Canada, T5M 2Z5 Ph: 780-481-1416 Client:
Project:
Project Location:
Sample Source:
Contact:

Boden Sand & Gravel
Aggregate Testing
N/A

Product #10, 20-15mm Round River Rock

__ Date: _ Project No.: _ Sample No.: _ Tech:

23-Jan-2024 02307211 2804 Connor C

ntact: Sana B

Sieve Analysis of Fine and Coarse Aggregates As Per ASTM C136/C136M

Moisture Content

Tare No.:	N/A
Wet Wt. + Tare (g):	N/A
Dry Wt. + Tare (g):	N/A
Tare Weight (g):	N/A
Moisture Content (%):	N/A

Sieve Analysis Sample

Tare No.:	B2
Dry Wt. + Tare (g):	6390.8
Wt. of Tare (g):	923.4
Dry Wt. of Sample (g):	5467.4
Adjusted Sample Wt. (g):	5467.4


Specification

Aggregate Analysis

Aggregate Analysis				
Sieve Size (µm)	Weight Retained (g):	Cumulative Weight Passing (g):	Passing (%)	
40 000	0.0	5467.4	100.0	
28 000	0.0	5467.4	100.0	
25 000	0.0	5467.4	100.0	
20 000	233.2	5234.2	95.7	
16 000	3165.5	2068.7	37.8	
14 000	1366.9	701.8	12.8	
12 500	451.8	250.0	4.6	
10 000	231.7	18.3	0.3	
5 000	11.1	7.2	0.1	
2 500	0.4	6.8	0.1	
2 000	0.2	6.6	0.1	
1 250	0.2	6.4	0.1	
630	0.3	6.1	0.1	
425	0.2	5.9	0.1	
315	0.3	5.6	0.1	
160	0.7	4.9	0.1	
80	0.9	4.0	0.1	

Dry Wash + Tare (g):

No Specification Given Min Max N/A 5463.6 Sample (g):



6387.0

0.6

Comments:	Material Sampled by Client, Material Delivered From Boden South Pit.

Data presented herein is for the sole use of the stipulated client. Englobe is not responsible, nor can be held liable, for the use made of his report by any other party, or without the knowledge of Englobe. The testing services reported herein have been performed by an Englobe technical no recognized industry standards, unless otherwise noted. No other warranty is made. This data does not include, or prepresent, any interpretation or opinion of specification compliance or meterial satisfaitily.



