

Product (#)

20-15mm River



Wet Weight Split 1	1549
Dry Weight Split 1	1518
Moisture Content	2.0%
Wet Weight Split 2	1499
Dry Weight Split 2	

Sample #	February 19 2025
Date & Time Sampled	February 19 2025
Sampled By	BSG
Date & Time Tested	February 19 2025
Tested By	BSG
Pit Location	Edberg

Sieve Size (µm)	Weight Retained	Fractured Weight	% Passing	Lower Limit	Upper Limit
25000	0	0	100.0		
20000	163	0	88.9		
16000	879		29.0		
12500	419		0.5		
5000	1		0.4		
2000	0		0.4		
1250	0		0.4		
80	3		0.2		
Pan	3				

Fractures (5mm +)	
Sieve Weights	1468
Fractured Weight	0
Fracture %	0.0%

The data represented in this report is for the sole use of the client. Boden Sand and Gravel is not responsible, nor can be held liable, for the use made of this report by any party, or without the knowledge of Boden Sand and Gravel. This data does not include, or prepresent, any interpretation or opinion of specification compliance or

Reviewed By: _____

