

Product (#)

40-20mm Screened



Wet Weight Split 1	1471
Dry Weight Split 1	1456
Moisture Content	1.0%
Wet Weight Split 2	1451
Dry Weight Split 2	

Sample #	February 19 2025
Date & Time Sampled	February 19 2025
Sampled By	BSG
Date & Time Tested	February 19 2025
Tested By	BSG
Pit Location	Boden

Sieve Number	Weight Retained	Fractured Weight	% Passing	Lower Limit	Upper Limit
50000	0	0	100.0		
40000	0	0	100.0		
25000	687	350	52.2		
20000	475	229	19.1		
12500	241	199	2.3		
10000	11	11	1.5		
5000	3	2	1.3		
2000	3		1.1		
160	4		0.8		
80	5		0.5		
Pan	6				

Fractures (5mm +)	(min 50%)
Sieve Weights	1417
Fractured Weight	791
	55.8%

The data represented in this report is for the sole use of the client. Boden Sand and Gravel is not responsible, nor can be held liable, for the use made of this report by any party.

