

2mm MF #19



Wet Weight Split 1	1223
Dry Weight Split 1	1202
Moisture Content	1.7%
Wet Weight Split 2	1177
Dry Weight Split 2	

Sample #	February 18 2025
Date & Time Sampled	February 18 2025
Sampled By	BSG
Date & Time Tested	February 18 2025
Tested By	BSG
Pit Location	Boden

Sieve Number	Weight Retained	% Passing	Lower Limit	Upper Limit
10000	0	100.0		
8000	0	100.0		
6300	0	100.0		
5000	0	100.0		
2500	17	98.5		
1250	211	80.3		
630	219	61.3		
315	168	46.8		
160	339	17.5		
80	187	1.3		
Pan	14			

