

Product (#)

2-40 (#2)



Wet Weight Split 1	1877
Dry Weight Split 1	1813
Moisture Content	3.5%
Wet Weight Split 2	1778
Dry Weight Split 2	

Sample #	03-Feb-25
Date & Time Sampled	February 3, 2025
Sampled By	BSG
Date & Time Tested	03-Feb
Tested By	BSG
Pit Location	Boden

Sieve Number	Weight Retained	Fractured Weight	% Passing	Lower Limit	Upper Limit
40000	0	0	100	100	100
25000	226	143	86.8	70	94
16000	445	287	60.9	55	85
10000	220	117	48.1	44	74
5000	142	103	39.8	32	62
1250	55		36.6	17	43
630	87		31.5	12	34
315	187		20.6	8	26
160	194		9.3	5	18
80	69		5.3	2	10
Pan	10				

Fractures (5mm +)	(min 50%)
Sieve Weights	1033
Fractured Weight	650
	62.9%

The data represented in this report is for the sole use of the client. Boden Sand and Gravel is not responsible, nor

