

# 4-20m Spec



Wet Weight Split 1	1563
Dry Weight Split 1	1551
Moisture Content	0.8%
Wet Weight Split 2	1577
Dry Weight Split 2	

<b>Sample #</b>	12-Feb-25
<b>Date &amp; Time Sampled</b>	February 12, 2025
<b>Sampled By</b>	BSG
<b>Date &amp; Time Tested</b>	February 12 2025
<b>Tested By</b>	BSG
<b>Pit Location</b>	Boden

Sieve Number	Weight Retained	Fractured Weight		% Passing
		1F	2F	
25000	0	0	0	100.0
20000	0	0	0	100.0
16000	223	160	139	85.7
12500	315	249	214	65.6
10000	217	175	153	51.8
5000	276	241	230	34.1
1250	195			21.7
630	61			17.8
315	69			13.3
160	90			7.6
80	56			4.0
Pan	8			

<b>Fractures (5mm +)</b>	1 Face	2 Face
Sieve Weights	1031	1031
Fractured Weight	825	736
	80.02%	71.39%

The data represented in this report is for the sole use of the client. Boden Sand and Gravel is not responsible, nor can be held liable, for the use made of this report by any party, or without the knowledge of Boden Sand and Gravel. This data does not include, or prepresent, any interpretation or opinion of specification compliance or material suitability.

