

Product (#)

4-30M



Wet Weight Split 1	1456
Dry Weight Split 1	1421
Moisture Content	2.5%
Wet Weight Split 2	1515
Dry Weight Split 2	1478

Sample #	February 7 2025
Date & Time Sampled	February 7 2025
Sampled By	BSG
Date & Time Tested	February 7 2025
Tested By	BSG
Pit Location	Boden

Sieve Number	Weight Retained	Fractured Weight	% Passing	Lower Limit	Upper Limit
25000	0	0	100.0		
20000	226	151	84.7		
16000	270	157	66.4		
10000	543	497	29.7		
5000	201	189	16.1		
1250	97		9.5		
630	25		7.8		
315	43		4.9		
160	41		2.1		
80	21		0.7		
Pan	9				

Fractures (5mm +)	(min 50%)
Sieve Weights	1240
Fractured Weight	994
	80.2%

The data represented in this report is for the sole use of the client. Boden Sand and Gravel is not responsible, nor can be held liable, for the use made of this report by any party, or without the knowledge of Boden Sand and Gravel. This data does not include, or present, any interpretation or opinion of specification compliance or material suitability.

