

Product (#)

40-20mm Washed



Wet Weight Split 1	1471
Dry Weight Split 1	1444
Moisture Content	1.9%
Wet Weight Split 2	1497
Dry Weight Split 2	

Sample #	February 19 2025
Date & Time Sampled	February 19 2025
Sampled By	BSG
Date & Time Tested	February 19 2025
Tested By	BSG
Pit Location	Boden

Sieve Number	Weight Retained	Fractured Weight	% Passing	Lower Limit	Upper Limit
50000	0	0	100.0		
40000	0	0	100.0		
25000	697	370	52.6		
20000	523	232	17.0		
12500	231	184	1.2		
10000	7	7	0.7		
5000	3	3	0.5		
2000	2		0.4		
160	1		0.3		
80	1		0.3		
Pan	4				

Fractures (5mm +)	(min 50%)
Sieve Weights	1461
Fractured Weight	796
	54.5%

The data represented in this report is for the sole use of the client. Boden Sand and Gravel is not responsible, nor can be held liable, for the use made of this report by any party.

